

Specification: ASTM D2000 M7BG910 A14 B14 EA14 EO14 EO34

Cure System: Sulphur

Recommended Service Temperature: -13 °F to 212 °F (-25 °C to 100 °C)

NOTES - All testing done on slabs and buttons. Material formerly known as N90R.

Original Properties	Specification	N90
Hardness, Shore A	90 +/- 5	88
Tensile Strength, psi	1450 (min)	2206
Ultimate Elongation, %	100 (min)	137
Specific Gravity		1.309
Color		Black
Heat Resistance - A14, ASTM D 573 (70 hrs @ 100 °C)		
Hardness Change, points	+/- 15	+3
Tensile Strength Change, %	+/- 30	+6
Ultimate Elongation Change, %	-50 (max)	-25
Compression Set - B14, ASTM D 395 Method B (22 hrs @ 100 °C)		
Permanent Set, %	25 (max)	10
Fluid Resistance, Water - EA14, ASTM D 471 (70 hrs @ 100 °C)		
Hardness Change, points	+/- 10	-5
Volume Change, %	+/- 15	+6
Fluid Resistance, ASTM #1 Oil - EO14, ASTM D 471 (70 hrs @ 100 °C)		
Hardness Change, points	+/- 5	+4
Tensile Strength Change, %	-25 (max)	+4
Ultimate Elongation Change, %	-45 (max)	-22
Volume Change, %	-10 to +5	-4
Fluid Resistance, IRM 903 Oil - EO34, ASTM D 471 (70 hrs @ 100 °C)		
Hardness Change, points	-10 to +5	-8
Tensile Strength Change, %	-45 (max)	-14
Ultimate Elongation Change, %	-45 (max)	-19
Volume Change, %	0 to +25	+9

The information contained herein is believed to be reliable, but no representation, guarantees or warranties of any kind are made to its accuracy or suitability for any purpose. The information presented herein is based on laboratory testing and does not necessarily indicate end product performance. Full scale testing and end product performance are the responsibility of the user.



DICHTOMATIK
AMERICAS

1087 Park Place
Shakopee, MN 55379
800-328-2840
www.dichtomatik.us