



Compound 4079

(colour: black)

General Description

Kalrez® 4079 is a carbon black filled compound having excellent chemical resistance and mechanical properties. It has a maximum operating temperature of 315°C, although short excursions to higher temperatures are possible. It exhibits low swell in organic and inorganic acids and aldehydes and has good response to temperature cycling effects. Kalrez 4079 has outstanding hot air ageing properties and exhibits very low and stable compression set at high temperatures. Its relatively low modulus can be a great help in assembly.

This is a general purpose material suitable for around 95% of all applications in all industries. Some of its uses are O-rings, diaphragms, seals, gaskets and other custom parts.

Compound 4079 is not recommended for applications involving water/steam and aliphatic amines at higher temperature. It should never be used in applications involving ethylene oxide or propylene oxide. The physical properties and chemical resistance of compound 4079 are as follows:

Physical Properties¹

Hardness ²	Shore A ± 5	75
100% Modulus ³	MPa	7,2
	psi	1050
TS at break ³	MPa	16,9
	psi	2450
Elongation at break ³	%	150
Compression set ⁴ , 70 h at 204°C	%	25

¹ Not to be used for specifications

² ASTM D2240

³ ASTM D412, 500 mm/min (20 in/min)

⁴ ASTM D395 B, pellets

Chemical Resistance

Material Compound	Kalrez 4079
<i>Chemical resistance to:</i>	
Aromatic / Aliphatic oils	+++*
Acids	+++*
Alkalis	+++*
Alcohols	+++*
Aldehydes	++
Amines	0
Ethers	+++*
Esters	+++*
Ketones	+++*
Steam / Hot Water	0
Strong Oxidizers	0
Ethylene / Propylene Oxide	--

+++ = excellent

++ = very good

+ = good

0 = marginal

-- = poor

--- = not recommended

* = recommended compound for this chemical

The major exceptions to the use of compound 4079 are listed below:

Hot water and steam

- Use Kalrez® 2035 up to 210°C.
- Use Kalrez 1050LF up to 280°C.
- Use Kalrez 3018 for high pressure applications.

Propylene/Ethylene oxide

- Use Kalrez 2035.

Hot aliphatic amines – above 80°C (the major aliphatic amines are ethylene diamine and hexamethylene diamine)

- Use Kalrez 3018 up to 280°C.
- Use Kalrez 1050LF up to 280°C.

Physical Properties

Specific gravity, g/cm ³	1,90 – 2,00
-------------------------------------	-------------

Miscellaneous

Oxygen – Autogenous Ignition Temperature	
Compound 1050 LF	313°C
Compound 1045	370°C

Permeation Rates of Gases

Gas	Nitrogen	Oxygen	Helium	Hydrogen	Argon	Krypton	Xenon
Temperature, °C	RT	RT	RT	93	93	93	93
Rate**	0,05	0,09	2,5	113	6,1	9,9	19,9

** × 10⁻⁹ cm³ - cm
s - cm² - cm Hg ΔP

Miscellaneous properties

Many miscellaneous properties are of interest for specific applications. Some of these are unaffected by compound choice while others vary with hardness or extensibility. As an example, coefficient of friction typically increases as hardness decreases.

In general, miscellaneous physical properties are similar to those of Viton® fluoroelastomer.

The following are some of the properties for Kalrez:

Thermal Properties

Linear coefficient of thermal expansion (25 – 250°C)

$$L = L_0 (1 + a\Delta T)$$
$$a = 2,3 \times 10^{-4}/^{\circ}\text{C}$$

Specific heat

at 50°C	= 0,945 J/g (0,226 cal/g)
at 100°C	= 0,974 J/g (0,233 cal/g)
at 150°C	= 1,053 J/g (0,252 cal/g)

For further information, please contact:

Global Headquarters

DuPont Dow Elastomers L.L.C.
300 Bellevue Parkway, Suite 300
Wilmington, DE 19809 USA
Tel. +1 302 792 4200
Fax. +1 302 892 7380

European Regional Headquarters

DuPont Dow Elastomers S.A.
2, chemin du Pavillon
CH-1218 Le Grand-Saconnex
Geneva, Switzerland
Tel. +41 22 717 4000
Fax. +41 22 717 4001

Asia Pacific Regional Headquarters

DuPont Dow Elastomers Pte Ltd.
1 Maritime Square #10-54
World Trade Centre
Singapore 099253
Tel. +65 275 9383
Fax. +65 275 9395

South & Central America Regional Headquarters

DuPont Dow Elastomers Ltda.
Rua Henrique Monteiro, 90
5 andar – Pinheiros
Sao Paulo – SP 05423-020
Brasil
Tel. +55 11 816 0256
Fax. +55 11 814 6845

Kalrez Parts Marketing

DuPont Dow Elastomers L.L.C.
P.O. Box 6098
Newark, DE 19714
Tel. 800 323 9806

Kalrez Parts European Marketing

DuPont Dow Elastomers N.V.
Battelsesteenweg 455d
B-2800 Mechelen, Belgium
Tel. +32 15 28 87 00
Fax. +32 15 28 87 50

Kalrez Parts Asia Pacific Marketing

DuPont Dow Elastomers Japan
Dempa Bldg
1-11-15 Higashi Gotanda
Shinagawa-ku, Tokyo
Japan
Tel. +81 3 3444 5166
Fax. +81 3 3444 6095



www.dupont-dow.com

The information set forth herein is furnished free of charge and is based on technical data that DuPont Dow Elastomers believes to be reliable. It is intended for use by persons having technical skill, at their own discretion and risk. The handling precaution information contained herein is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards. Since conditions of product use and disposal are outside of our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. As with any material, evaluation of any compound under end-use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate or a recommendation to infringe on any patents.

CAUTION: Do not use in medical applications involving permanent implantation in the human body. For other medical applications, discuss with your DuPont Dow Elastomers customer service representative.

Kalrez® and Viton® are registered trademarks of DuPont Dow Elastomers.
Copyright © 1999 DuPont Dow Elastomers. All rights reserved.

