

# PK701 (ACM)

# Material Properties

Specification: ASTM D2000 M3DH710 A26 B36 EO16 EO36

Recommended Service Temperature: -13 F to 302 F (-25 C to 150 C)

Original Properties	Specification	PK701
Hardness, Shore A	70±5	70
Tensile Strength, Mpa	10 (min)	10.4
Ultimate Elongation, %	200 (min)	221
Tear Strength (kg/cm)		30
Specific Gravity		1.41

  

Heat Resistance - A26 (70 hrs @ 150 C)		
Hardness Change, points	+10 (max)	+3
Tensile Strength Change, %	-25 (max)	+4
Elongation Change, %	-30 (max)	-2
Volume Change, %		-1

  

Compression Set, % - B36 (22 hrs @ 150 C)		
Permanent Set, %	+50 (max)	+38

  

Fluid Resistance, ASTM #1 Oil - EO16 (70 hrs @ 150 C)		
Hardness Change, points	-5 to +10	0
Tensile Strength Change, %	-20 (max)	+6
Elongation Change, %	-30 (max)	-7
Volume Change, %	-5 to +5	-1

  

Fluid Resistance, IRM 903 Oil - EO36 (70 hrs @ 150 C)		
Hardness Change, points	-15 (max)	-8
Tensile Strength Change, %	-30 (max)	-5
Elongation Change, %	-30 (max)	+5
Volume Change, %	+25 (max)	+10

The information contained herein is believed to be reliable, but no representation, guarantees or warranties of any kind are made to its accuracy or suitability for any purpose. The information presented herein is based on laboratory testing and does not necessarily indicate product performance. Full scale testing and product performance are the responsibility of the user.



1087 Park Place, Shakopee, MN 55379  
800-328-2840 • www.dichtomatik.us

**O-Rings • Rotary Shaft Seals • Fluid Power Seals • Custom Molded Shapes  
Fitting & Fastener Seals • Spliced Rings & Extruded Cord**